

蜡浆

产品介绍

DeuWax W-2340 为一水性蜡浆，无需研磨可以在调墨的任何阶段添加，搅拌均匀后稳性细好。对油墨的光泽影响很小，却可提供极佳的耐磨性和滑度。

在正常情况下没有再涂性问题，而可提供一定的拨水性。

产品特征

组成	聚烯烃混合蜡
外观	乳白色流动液体
不挥发份	38.5 - 41.5%
比重	约 1.03
pH 值	7 - 8
细度	<20 μm

应用领域

- 水性柔性版油墨
- 水性凹版油墨
- 水性丝网油墨
- 水性涂料

主要特性

- 改善水性涂料及油墨的耐磨性及提供滑感。
- 对涂膜光泽影响小。
- 无须研磨，可后添加。
- 在正确用量下，不影响再涂。

使用方法

- 可在任何阶段添加。
- 请试验最适添加量。

添加量

对全量添加 0.2 - 3.0%。

储存与安全

小心操作，避免接触皮肤和眼睛。其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存条件为 2°C 至 40°C。若储存于 0°C 以下有结冻状态时，需解冻(温度 <40°C)并均匀搅拌分散后才可使用。
- 储存长时间后可能有分层现象产生，应搅拌均匀后取用。

包装

净重：20 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B02 Mar-10

有效期

DeuWax W-2340 自生产日起，保质期限为 6 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
china 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213