

附着增进剂



产品介绍

Hardlen 163-LR PP 用特殊树脂，能充当底漆或添加于面漆使用，彻底解决涂料在未处理 PP 底材上附着不良的困扰。

产品特征

组成	氯化 PP 改性丙烯酸树脂
外观	微浊液体
不挥发份	43 - 47%
溶剂	甲苯 / 二甲苯
比重	约 0.9
粘度	2700 - 6300 cP

应用领域

- 将 Hardlen 163-LR 调整至适当粘度即可直接施涂于 PP 材质的表面，也可以加入颜料经研磨后制成有颜色的涂料而无损原先的附着性能。
- 可以当做一般丙烯酸或聚氨酯涂料的底漆使用。
- 在 Hardlen 163-LR 中加入对全量 10 - 20% 的 PPB，更能增进 Hardlen 163-LR 对 PP 底材的附着性。
- 无论是采用何种方式来使用，喷涂后若再以 80 - 85°C 烘烤约 30 分钟，可使附着性大幅提升。

主要特性

直接或与丙烯酸树脂混合，做为底漆或色漆喷涂在 PP 材质上。

使用方法

- 作为汽车内部用一次涂装的单组份面漆。
- 加入颜料研磨直接做成底色漆。
- 一般丙烯酸或聚氨酯涂料的底漆。

添加量

—

操作与安全

- 本产品在经过长时间储存后，可能因为溶剂挥发或低温导致于粘度上升甚至胶化，若发生此种现象，请补充溶剂并以水浴方式加热使其恢复原状，并在最短时间内使用完毕。
- 加入丙烯酸树脂中，需先试验相容性。
- 本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 10°C 至 40°C。

包装

净重：25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

—

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213