

附着增进剂

产品介绍

Hardlen F-2P 为特殊酸改性氯化聚烯烃，相容性佳，对 PP 底材附着性佳。

产品特征

组成	改性氯化聚烯烃
外观	微黄色粒状
不挥发份	约 100%
粘度	25 - 200 cP (25°C, 20%甲苯溶液)
氯含量	19 - 21%

应用领域

PP 底材用底色漆

主要特性

- Hardlen F-2P 应用于聚烯烃底材的底色漆中，不需任何电浆，火焰和溶剂清洗之类的预处理。
- 低烘烤温度之附着性优异。
- 与其他树脂相容性佳。
- 屈挠性佳。

使用方法

可单独使用或与其它较高极性树脂混合拼用作成底色漆。

添加量

将 Hardlen F-2P 于搅拌状态下加入甲苯中，加热溶解至均匀无颗粒之溶液，冷却后即可使用。建议可溶成 10 - 30% 再使用，超过 30% 其粘度太高不易操作。

操作与安全

小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：20 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Hardlen F-2P 自生产日起，保质期限为 24 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213