

## 消泡剂

### 产品介绍

Defom 3500 为不含硅酮高分子型消泡、脱泡剂，适用于溶剂型或无溶剂涂料体系。主要为抑制或消除木器底漆因制造过程或内含填充料所导致的气泡。

### 产品特征

组成	破泡聚合物，不含硅酮
外观	澄清液体
不挥发份	19 - 21%
溶剂	脂肪族碳氢溶剂 / 羟基乙酸丁酯 / 乙二醇单丁醚
比重	约 0.80

### 应用领域

- 木器底漆
- 硝基漆
- 聚氨酯二度底漆
- 木器手刷漆

### 主要特性

- 抑制木器底漆内含硬脂酸锌等，高起泡性的填充料所产生的气泡。
- 对于高粉料木器底漆，具有优异抑泡性。
- 对于手刷漆，因施工粘度较高流动性差，所造成的气泡能容易破除。
- 多孔性的底材如纸张、木材等，在涂装时常造成空气残留在涂膜底部或内部，添加 Defom 3500 可以帮助涂料的润湿，减少气泡的残留。

### 使用方法

在粉料前添加，可得最佳效果。

### 添加量

对全量 0.1 - 0.5%。

### 操作与安全

- 本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。
- 本产品长期储存后，外观可能会有色差变化，呈微黄色或微红色，此变化不影响物料性能。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

### 包装

净重：160 kg / 20 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B02 Jan-10

## 有效期

Defom 3500 自生产日起，保质期限为 12 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213