

## 润湿分散剂

### 产品介绍

Disponer 903 适用于溶剂型涂料的防发花、浮色添加剂。

### 产品特征

组成	改性聚硅氧烷
外观	澄清液体
不挥发份	8.5 - 10.5%
溶剂	二甲苯/异丁醇
比重	约 0.85
折射率	1.462 - 1.472 (25°C)

### 应用领域

- 调合漆
- 醇酸/胺基树脂
- 聚酯/胺基树脂
- 丙烯酸/胺基树脂
- 硝基漆
- 双组份聚氨酯涂料

### 主要特性

- 防止涂膜产生贝纳德窝。
- 消除多颜料体系的浮色、发花及丝纹现象。
- 调色时添加可避免颜色不均匀的现象。
- 增进涂膜的流平性、流动性与光泽度。
- 与大多数的涂料体系相容。
- 少量添加即具有效果。

### 使用方法

通常在研磨后或调色时添加，亦可在研磨前添加，帮助颜料的润湿。

### 添加量

对全量添加 0.1 - 1.0%

### 操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤和眼睛。其它资料请参考物质安全资料表。

### 储存条件

- 远离热火星及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 容器打开后未使用完毕，需密封完全，防止水气进入。

### 包装

净重：180 kg/25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Nov-09

## 有效期

Disponer 903 自生产日起，保质期限为 18 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213