

润湿分散剂

产品介绍

Disponer 923 为适用于中低极性溶剂型涂料的润湿、分散。

产品特征

组成	电中性聚羧酸胺盐
外观	棕色微浊液体
不挥发份	48 - 52%
溶剂	芳香族碳氢溶剂
比重	约 0.89
折射率	1.488 - 1.498 (25°C)

应用领域

- 调合漆
- 环氧涂料
- 醇酸/胺基树脂
- 酸固化
- 氯化橡胶

主要特性

- 适合作为溶剂型涂料中各种无机颜料的润湿分散剂。具特殊的界面活性，能帮助颜料的润湿及解絮凝，因此大幅缩短分散时间。能吸附在颜料表面防止返粗，使涂料具有良好的储存安定性。
- 是膨润土良好的活化剂，添加 Disponer 923 的膨润土预凝胶具有下列优点：
 - 缩短分散时间
 - 可调整粘度，操作方便
 - 增进防沉、防流挂性
 - 改善储存安定性

使用方法

作为分散剂：于研磨前添加。

添加量

- 作为分散剂
对颜料量 0.5 - 2.0% 研磨前添加。
- 作为膨润土活化剂
对膨润土量 30 - 50%。

操作与安全

- 本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。
- Disponer 923 使用于硝基漆时，可能造成变色。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 5°C 时，外观可能混浊或分离，请加热到澄清状态，搅拌均匀后使用。
- 容器打开后，未使用完毕需完全密封。

包装

净重：180 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Disponer 923 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213