

UV 硬化寡聚物

產品介紹

Hypomer VP-UR-803 是設計用於塑料塗裝的聚氨基丙烯酸酯。特別適用於真空鍍 UV 面漆。

產品特徵

組成	聚氨基丙烯酸酯
外觀	黃棕色黏稠液體
色度	<8 Gardner
不揮發份	59 - 63%
溶劑	乙酸正丁酯
比重	約 1.1
黏度	500 - 2000 cP (25°C)
折射率	1.461 - 1.465

應用領域

- UV 硬化塗料與油墨
- 塑料塗料

主要特性

- 耐水性
- 硬化速度快

使用方法

當作塗料中的添加樹脂，搭配稀釋單體，光起始劑，與溶劑配成塗料。

添加量

建議對塗料固成份 10 - 20%。

操作與安全

本產品含有溶劑，須小心操作，避免接觸皮膚與眼睛，其它資料請參考物質安全資料表。

儲存條件

- 遠離熱及火源。
- 置於陰涼通風處，容器保持緊密。
- 儲存環境為 0°C 至 40°C。

包裝

淨重：200 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Feb-10

有效期

Hypomer VP-UR-803 自生產日起，保質期限為 12 個月。

品質保證

本公司自 1992 年起獲得 ISO 9001／9002 品質系統認證，確保所有操作符合標準規定。

海名斯特殊化學，亞洲

Head Office

上海市松江工業區聯陽路 99 號
郵編 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹縣湖口鄉新竹工業區光復北路
92 號
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213