

## 附着增进剂

### 产品介绍

Adherent ADP 为添加于烘漆底漆或一次涂装烘漆，以增进对非铁金属表面的附着性。

### 产品特征

组成	不含聚硅氧烷化合物
外观	澄清液体
不挥发份	78 - 82 %
溶剂	异丙醇
比重	1.08 - 1.10
酸价	60 - 80 mg KOH/g

### 应用领域

- 醇酸/胺基树脂烘漆
- 丙烯酸/胺基树脂烘漆

### 主要特性

- 改善对难附着的非铁金属表面的附着性有极优异的效果。
- 可增进涂膜的延展性与耐冲击性。
- 高温急速烘烤不变色，并且不影响涂膜的耐候性。
- 不影响涂料的储存安定性。

### 使用方法

研磨前、后添加均可，直接用于底漆时，添加量因树脂附着性而定，使用前请预先试验。

### 添加量

对全量 1.5 - 2.5%

### 操作与安全

- 本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。
- Adherent ADP 含有酸性结构，若与某些碱性颜料混合使用会有消光现象产生，请使用前预先试验。
- Adherent ADP 储存于低温下会产生混浊或分离状况，请加热搅拌至澄清即可使用，并不会影响产品性能。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 低于 5°C 时，外观可能结冻，混浊或分离，请水浴加热至澄清状态，搅拌均匀后使用。

### 包装

净重：200 kg / 25 kg

### 有效期

Adherent ADP 自生产日起，保质期限为 18 个月。

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Nov-09

## 品质保证

本公司自 1992 年起获得 ISO 9001 / 9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213