

## 润湿分散剂

### 产品介绍

Disponer 929 是针对碳黑而发展出来的分散、展色剂，可添加在涂料内研磨；或作为研磨展色剂，单独与碳黑混合研磨分散，作成调色或着色用黑色浆。

### 产品特征

组成	阴离子性高分子型界面活性剂
外观	淡黄色澄清液体
不挥发份	48 - 51%
溶剂	二甲苯 / 芳香族碳氢溶剂 / 乙酸正丁酯
比重	约 0.97
折射率	1.484 - 1.494 (25°C)

### 应用领域

- 调和漆
- 醇酸 / 胺基树脂
- 溶剂型凹版和丝网油墨

### 主要特性

- 储存安定性优异，防止颜料絮凝的发生，保持粘度与细度的稳定。
- 研磨分散液粘度低，能制成高颜料浓度的色浆或涂料。
- 提高涂料和油墨的展色性和透明度。
- 制成复色漆时，不易浮色、发花。

### 使用方法

- 研磨前添加与颜料一起分散。

### 添加量

- 作为研磨展色剂时，对全量添加 20 - 50%。
- 作为分散剂时，对碳黑添加 20 - 80%。

### 操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

### 储存条件

- 远离热火星及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 5°C 时外观可能结冻或混浊状，请隔水加热至澄清状态再搅拌均匀方可使用。

### 包装

净重：180 kg / 25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

® Trademark of Elementis Specialties, Inc.

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Nov-09

## 有效期

Disponer 929 自生产日起，保质期限为 18 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213