

水油通用防霉剂

产品介绍

DeuAdd MB-16 为一广效性的防腐剂产品。可提供优异的杀菌、防霉效果。在水性体系可广泛应用。

产品特征

组成	杂环化合物
外观	微黄色至棕色澄清液体
不挥发份	7 - 9%
溶剂	芳香族碳氢溶剂 / 乙二醇单甲醚
比重	0.90 - 0.93
水溶性	可分散于水中
pH 值	6 - 7 (100 PPM 水中)

应用领域

- 水性涂料体系
- 溶剂型涂料体系

主要特性

- 能有效抑制霉菌、细菌的滋生，防止涂膜变色或涂料变质，在高湿度的环境下效果尤其显著。
- 不含汞或重金属，毒性低。
- 在水中溶解度极小，可提供有效的涂膜防霉效果。
- 不与大气中的硫化物反应，涂膜不会变黑。
- 适用性广，在水性、溶剂型体系均可使用。
- 产品呈液态，使用方便。

使用方法

可在涂料制造的任何阶段添加，一般先在研磨时添加一部份，余者在调整时添加，可获得最佳效果。

添加量

添加量视环境、体系及需求而定。一般为对全量 0.1 - 0.5%；对防腐、防霉有特别要求时，添加量在 0.5 - 2.0%（对全量）；涂膜的防霉效果是随着 DeuAdd MB-16 添加量的增加相应提高，具体添加量请依所应用条件先行测试

操作与安全

- 小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。
- 使用体系的 pH 值应不大于 8.5。
- 勿与一级胺或二级胺直接接触。
- 钴催干剂会与 DeuAdd MB-16 反应，请改用锰或铅催干剂。
- 不可使用在环境卫生或污染防治上。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 5°C 至 40°C。

包装

净重：170 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

DeuAdd MB-16 自生产日起, 保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证, 确保所有操作符合标准规定。

海名斯特殊化学, 亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213