

## 水性流变助剂

### 产品介绍

DeuRheo WT-115 为一疏水改性碱溶胀型丙烯酸乳液增稠剂，提供水性体系增稠、流动、保水等效能。

### 产品特征

组成	阴离子型丙烯酸聚合物 (HASE)
外观	白色或粉红色液体
不挥发份	29 - 31%
溶剂	水
比重	约 1.04
粘度	≤ 20 cP (25°C)
pH 值	3 - 5 (原液)

### 应用领域

- 乳胶漆
- 水性涂料
- 纺织涂料
- 水性丝网油墨
- 水性粘合剂

### 主要特性

- 有效提升中剪粘度，触变性较小。
- 提供很好的流动、较好的流平性能。
- 保水性、相容性好，易于调色。
- 在碱性环境下，产生增稠效果。
- 不含有机溶剂和烷基酚聚氧乙烯醚 (APEO)，可用于环保型产品的制备。

### 使用方法

- 应用时可与其它流变助剂搭配以获致所需的流变性能。
- 将 DeuRheo WT-115 用水稀释后 (DeuRheo WT-115 / 水 = 1 / 1 - 5) 加入体系，且充分搅拌均匀，并用 DMAE 调整体系的 pH 值至 7.5 - 10.0。

### 添加量

对全量添加 0.1 - 2.0%。

### 操作与安全

小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，避免阳光照射。
- 避免受冻而造成破孔。
- 建议在 5°C - 40°C 环境条件下使用和储存。
- 取用后如未使用完需盖紧密封盖以防结皮。

### 包装

净重：25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Jan-10

## 有效期

DeuRheo WT-115 自生产日起, 保质期限为 12 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证, 确保所有操作符合标准规定。

---

### 海名斯特殊化学, 亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213