

水性消泡剂

产品介绍

DAPRO[®] DF 1760 是一高效能且不含有有机硅长效型消泡剂。即使涂料长期存放后使用，仍可维持其有效的消泡性能。

DAPRO[®] DF 1760 所含的所有非挥发性成分皆符合美国联邦法规的药物暨食品管理 (FDA) CFR 21 175.105; 175.300; 176.170 与 176.180 条款的规定。

产品特征

| | |
|-------|--------|
| 活性份 | 100% |
| 外观 | 澄清液体 |
| 闪点 | 110°C |
| 每加仑重量 | 8.2 lb |
| 比重 | 1.01 |

应用领域

- 罐头涂料
- 汽车原厂漆 (OEM) 与汽车修补漆
- 工业防护涂料
- 卷材涂料
- 木器涂料
- 水墨与各种紫外光体系

主要特性

- 抑泡消泡速度快，长效性好
- 对涂料光泽不会产生不良影响
- 可于广泛的 pH 值范围内使用
- 添加容易
- 不含芳香族化合物或矿物油

使用方法

DAPRO[®] DF 1760 消泡剂使用前应充分混合均匀，可直接加入至研磨浆料部分或调漆阶段。如需添加到成品漆中，须特别小心，以确保其均匀分布。

添加量

当 DAPRO[®] DF 1760 的添加量占配方总量的 0.2 - 0.6% 时，就可获得理想的效果。

操作与安全

每种产品均有操作与安全性方面的详细资料。在使用该产品前请参阅相关的物质安全资料表 (MSDS)。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境温度为 5°C 至 50°C。

包装

DAPRO[®] DF 1760 可提供桶装与散装形式。请与您所在当地海名斯特殊化学的代表联系，选用适合当地的具体包装形式和包装重量。

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Jan-10

有效期

DAPRO® DF 1760 自生产日起, 保质期限为 24 个月。

质量保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证, 确保所有操作符合标准规定。

海名斯特殊化学, 亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213