

蜡浆

产品介绍

DeuWax FA-110 为一优异的消光浆可降低涂膜光泽，并有促进涂面平滑的效用。

产品特征

组成	聚乙烯蜡
外观	白色流动浆状
不挥发份	9.5 - 10.5%
溶剂	二甲苯 / 乙酸正丁酯
比重	约 0.88

应用领域

- 皮革涂饰
- 硝基漆
- 喷漆
- 聚氨酯涂料
- 溶剂型油墨

主要特性

- 无需研磨，分散极易，直接加入成品，搅匀即可。
- 悬浮性良好，不似一般消光粉易发生沉降现象。
- 具有消光性，雾面柔细、透明、滑润，触感极佳，绝不似消光粉所造成的混沌现象与指甲刮过留下痕迹的情形。
- 耐久不泛黄。

使用方法

- 添加时需以高速分散设备分散均匀。
- 本产品由于触变性高，储存时可能发现上下粘度不均匀，此系正常现象，使用前请搅拌均匀，并尽可能整桶使用。
- 若遇蜡浆密闭不严所产生的干涸、结皮、结块等现象，需将此干涸部份去除，以免造成分散困难。

添加量

- 消光：对全量添加 10 - 20%。
- 完全消光：需配合消光粉使用。

操作与安全

本产品含有溶剂，须小心操作，避免接触皮肤与眼睛。其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C 间（需回复至 25°C 方可使用）。
- 盛放产品的容器不能直接受到热辐射。

包装

净重：170 kg / 15 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

DeuWax FA-110 自生产日起，保质期限为 12 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213