

## 蜡浆

### 产品介绍

DeuWax 2310 为一预分散聚乙烯蜡浆，可赋予涂膜较佳的耐磨耗及抗刮伤性能。

### 产品特征

组成	聚乙烯蜡
外观	白色至微黄色浆状
不挥发份	9.5 - 10.5%
溶剂	甲苯 / 乙酸正丁酯
比重	约 0.88

### 应用领域

- 双组份丙烯酸聚氨酯涂料
- 丙烯酸喷漆
- 硝基漆
- 紫外光固化涂料
- 凹版油墨

### 主要特性

- 适用于较高光泽涂料体系。
- 提高涂膜耐磨耗性及抗刮伤性。
- 提供涂膜防贴合性及表面平滑性。
- 贴花离型性佳。

### 使用方法

- DeuWax 2310 使用前请先搅拌均匀，后添加并以中等转速之分散设备加以分散。
- 请试验最适添加量。

### 添加量

对全量添加 1 - 5%。

### 操作与安全

本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

### 包装

净重：170 kg / 15 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Jan-10

## 有效期

DeuWax 2310 自生产日起，保质期限为 12 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213