

[®] Resimene 755

Technical Data Sheet

CHARACTERISTICS

Hexamethoxymethyl/n-butyl- melamine formaldehyde resin

STRUCTURE

FORM OF DELIVERY

Min. 98 solvent free

SPECIFICATION

Determined per batch

Property

Viscosity DIN EN ISO3219-B

Cone & Plate 435-1061-1 (25°C) CPS] 700-1150 Gardner-Holdt 25°C (435-1200-3) T - W

Non-Volatile Matter

(Foil,45min at 45°C) (435-1200-19) [%] >98

Color, APHA (435-1019) 30 max.

Haze, APHA (435-1019) 5 max.

Density (Liquids) (435-1200-30) at 25°C LB./Gal. 9.0- 9.2

Formaldehyde Content (Sulfite)
(435-1205) [%] 0.1 max.

Not continually determined

Flash Point (Pensky Martens)

analog.DIN EN 22719

°F >230

[°C] [>110°]

Degree of polymerisation, DP (GPC/PSI) 1.30

USES:

Resimene 755 is a mixed methylated-butylated (55/45) melamine resin, which results an improved flow, leveling and cratering resistance in coating formulations, plus better intercoat adhesion.

Resimene 755 provides excellent overall catalyzed cure performance attributes, particularly in the areas of flexibility, adhesion, durability, and water/chemical resistance like automotive high solid primers, base and clear coats. Additionally, Resimene 755 could be used in waterborne coatings esp. anodic electrodeposition coatings (incl. Ultrafiltration)

STORAGE STABILITY:

At temperatures up to 25°C the storage stability of Resimene 755 packed in original containers amounts to at least 24 months.

Some turbidity may occur in isolated cases but this has no effect on product quality.



INEOS Melamines

	World Area	Customer Order	Technical Support
INEOS Melamines, Inc. 1395 S. Marietta Parkway Bldg. 500, Suite 210 Marietta, GA 30067	North America	+1888 723 2873 +1770 528 6693	+14137302757 +14137303444
	South America	+1678 999 3172 +1770 528 6693	+14137302757 +14137303444
INEOS Melamines GmbH Alt Fechenheim 34 D 60386 Frankfurt, Germany	Europe-Africa	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
www.ineosmelamines.com	Asia Pacific	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines Inc. (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Ineos Melamines Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines Inc.