# INEOS Melamines

## <sup>®</sup> MAPRENAL MF 988/80B

Very high flexibility and gloss and therefore suitable for can-, packaging


## **Technical Datasheet**

#### TYPE

Imino type, reactive, n-butylated benzoguanamine-formaldehyde resin

#### FORM OF DELIVERY (f.o.d.)

80 % in n-butanol (80B)



coatings and automotive primers.

**FILM PROPERTIES / CLEAR COAT** 

STRUCTURE

USES

### **PRODUCT DATA**

Determined per batch:

#### Viscosity EN ISO 3219-B

(23 °C)	[mPa.s]	5000 - 10000		
Non-Volatile Matter DIN EN ISO 3251				
non-volatile matter analogue DIN EN ISO 3251 (1 h; 120 °C; 2 g; IB)	[%]	78 - 82		

#### Compatibility (aliph. hydrocarbon) DIN EN ISO 11908

Compatibility (anpin nyai ocai bony					
dilutability (n-Heptan) (23 °C)	[ml/g]	0,5 - 2,5			
Not continually determined:					
lodine Colour Number DIN 6162					
iodine colour number		< 1			
Density (Liquids) DIN 12791 part 1+3					
density	[g/ml]	1,10			

#### (20 °C) Flash Point (Pensky-Martens) DIN EN 22719

flash point [' analogue DIN EN 22719 approx.	°C]	48	

#### Formaldehyde Content (Sulfite) DIN EN ISO 11402


content	[%] 0,9
approx.	

## degree of polymerisation, DP

(GPC/PSI)

approx.

Film properties clear coat



Maprenal MF 988/80B(AC/MF = 70/30)

#### STORAGE

At temperatures up to 25 °C storage stability of Maprenal MF 988/80B packed in original containers amounts to at least 12 months. Some turbidity may occur in isolated cases but this has no effect on product quality.

Data contained in this publication are based on carefull investigations and are intended for information only. Any user is obliged to carry out tests under his own responsibility as to suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products as established by law. Any liability as to the exactness and completeness of data is thus excluded. We apply our General Sales Conditions.

1.4

## INEOS Melamines

	World Area	Customer Order	Technical Support
<b>INEOS Melamines, Inc.</b> 1395 S. Marietta Parkway Bldg. 500, Suite 210 Marietta, GA 30067	North America South America	+1888 723 2873 +1770 528 6693 +1678 999 3172 +1770 528 6693	+ 1 413 730 2757 + 1 413 730 3444 + 1 413 730 2757 + 1 413 730 3444
<b>INEOS Melamines GmbH</b> Alt Fechenheim 34 D 60386 Frankfurt, Germany	Europe-Africa	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
www.ineosmelamines.com	Asia Pacific	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines Inc. (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Ineos Melamines Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines Inc.