

Opacilite™

Opacilite is a high whiteness calcined kaolin produced by a special rapid heating process. This process creates large numbers of tiny, sealed voids within the kaolin particles, resulting in a low specific gravity and outstanding opacifying properties. The presence of these sealed voids differentiates **Opacilite** from conventional calcined kaolins.

SPECIFICATION

		Opacilite
Brightness	(ISO R 457)	87.0 ± 1.0
+53µm	(mass % max.)	0.05
- 2µm	(mass %)	55 ± 7.0
Dispersion,	(µm max.)	35
Specific Gravity		2.06 ± 0.06
Moisture	(mass % max as produced)	0.5

TYPICAL PROPERTIES

Yellowness		3.7
Oil absorption	(g/100g)	74
Aerated powder density	(kg/m ³)	260
Tapped powder density	(kg/m ³)	480
- 1µm	(mass %)	25
+10µm	(mass %)	5

EINECS No. 296-473-8

CAS No. 92704-41-1

DAT104CK

March 2008
©IMERY'S Minerals Ltd - 2008

Ninth edition - This data sheet supersedes the data sheet dated January 2007

Opacilite™ is a trademark of IMERY'S Minerals Ltd



ISO 9001
FM 14752

IMERY'S

Par Moor Centre,
Par Moor Road, Par
Cornwall, England
PL24 2SQ
Tel: +44 1726 81 8000
Fax: +44 1726 81 1200

IMERY'S is a business name of IMERY'S Minerals Ltd

The data quoted are determined by the use of IMERY'S Minerals Ltd Standard Test Methods, copies of which will be supplied on request. Every precaution is taken to ensure the products conform to our published data, but since the products are based on naturally occurring raw materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our 'Conditions of Sale', copies of which will be supplied on request.

